

Polyester Imide Varnish

NAME OF ENAMEL	THERMAL CLASS	SOLID CONTENT %	VISCOSITY (POISE)	APPLICABLE WIRE DIA. mm	SUITABLE OVEN TYPE	COATING METHOD	FEATURES
YKH303	F~H	33~43	1.5~65	0.3~2.0	H、V	D	Wild working conditions.
YKH305	F~H	25~40	0.5~35	0.1~2.0	H、V	F、D	Improved Heat Shock.
YKH306	F~H	40	10~20	0.5~2.0	H、V	D	Improved Heat Shock.
YEI342S	H	38~40	30~50	0.5~2.0	V	D	Great Solderability.
YEI343S	H	38~40	30~50	0.5~2.0	V	D	Improved Cut Through.
YEI350	H	33~40	3~35	0.3~2.0	H、V	D	Great Heat Shock.
YEI355	H	33~40	2~25	0.3~2.0	H、V	D	Wild working conditions.

※H : HORIZONTAL OVEN V : VERTICAL OVEN F : FELT D : DIES