

Modifide Polyimide Varnish

NAME OF ENAMEL	THERMAL CLASS	SOLID CONTENT %	VISCOSITY (POISE)	APPLICABLE WIRE DIA. mm	SUITABLE OVEN TYPE	COATING METHOD	FEATURES
YPI420	C	14	0.4~0.7	0.1~0.3	H	F	Improved Stability. Improved Pinhole resistance. Improved Heat Shock. Improved Cut Through. Wild working conditions.
		18	0.8~1.2	0.3~0.6	H	F · D	
		24	4~8	0.3~1.0	H	D	
		28	9~15	0.5~1.6	V	D	

※H : HORIZONTAL OVEN V : VERTICAL OVEN F : FELT D : DIES